Self-adhesive Bitumen Membrane





WD Cross-laminated Smooth



Description:

Weidun® WD002 Self-adhesive Membrane is a self-adhesive bituminous sheet waterproofing membrane. It's based on a SBS modified bitumen compound on a cross-laminated film, formulated for hot and tropical climate.

Uses:

Weidun®WD002 Self-adhesive Membrane is designed for outside of external wall and re-cover applications as well as in the construction of flashings, especially for projects that open flame is prohibited. Weidun®WD002 Self-adhesive Membrane is an ideal product in Weidun self-adhesive modified bitumen systems.

Advantages:

- Durability The membrane combines the strength of fiberglass reinforcement with the elongation charactristics of SBS modified bitumen.
- Cold apply No torch or open flame required.
- Save labor rolls out flatter and provides easy installation.
- Lighter weight The membrane weigh less than 4kgs per square meter.
- Product warranties and systmen guarantees are available. Contact your sales representative for detailed information.

Product Application:



Storage and Handing:

To prevent damage, support rolls on end in an upright position and store ina clean, dry location, covering as necessary to protect from environment damage. Monitor environmental conditions during storage, handling, and application.





Product Specifications:

Roll Size*	10.0 m²
Roll Length	10.0m
Roll Width	1.0m
Roll Thickness	3.0mm; 4.0mm
Rolls per Pallet	30
Full Pallet Weight	1.2 ton
Top side Surfacing	Film or Aluminum
Bottom Side Surfacing	Film

Note: Actual membrane dimensions are customizable, please contact your sales representative for support.

Technical Data Sheet:

Property	Standard Minimum Value	Weldun Value
Thickness min, mils(mm)	>1.5	1.6
Length min, meter(m)	>9.99	10.07
Tensile strength at 23°C +/-2 (N/50mm)	>200	278
Elongation at break at 23°C +/-2°C, (%)	>30	48
Tear strength at 23°C +/-2°C (N/50mm)	25	35
Peal strength of membrane and mortar (N/mm)	>1.5	1.6
Low-temperature flexibility, at -20 °C	No crack	No crack
Heat resistance, at 70°C, 2hours	No drop	No drop
Time of adhesion (minutes)	30	45
Overlap peel strength (N/mm)	>1	1.2
Water penetration(Maintain a water pressure of 0.3Mpa for 30 minutes)	Non-penetration	Non-penetration

